MINROCK

Rockwool Sectional Pipe Insulation

Product Description

Minrock rockwool Sectional Pipe Insulation (SPI) consists of fine fibres spun from molten natural rock bonded with a thermosetting resin. The sections are moulded to ensure a firm fit around the piping and the outer surface is ground to ensure that correct insulation thickness is achieved and to provide a smooth, even surface.

Minrock rockwool SPI products are available for hot face temperatures upto 750°C. Minrock rockwool SPI are supplied as one - piece sections of one metre length, upto 4"N.B. and with slit along the longitudanal axis in two sections for 4" N.B. and above. Sections are easily installed by opening the slit and springing the section into position over the pipe.



Minroc^L Pipe Section Conforming to IS 9842

Applications

Minrock rockwool SPI is used on both hot and cold piping to conserve energy, maintain, process temperatures, provide personal protection, prevent condensation, and to reduce noise emission. Minrock rockwool SPI

should be retained by wire or metal bands in accordance with the manufacturer's recommendations, and protected if required by metal cladding, mastic or other suitable coating.

Standard Size and Packing

Pipe nominal Bore Wall Thickness Length 15 mm to 350 mm 25mm to 100mm

Standard Packing

Cardboard cartons The number of sections per pack depends on the size of the section

Density (Kg/Cu.m.)

144


1000mm

Maximum Service Temperature

750°C

Thermal Conductivity

The thermal conductivity of Minrock rockwool SPI varies with the mean temperature of the insulation as shown in the graph. The curve is based on measurements made with a guarded hot-plate apparatus in accordance with IS 3346-1992



Thermal Conductivity (W/m.K) x Mean Temperature (OC)

MINROCK

Compression Resistance

Minrock rockwool SPI is a resilient insulation material which readily

reocovers to its nominal thickness after the removal of a normal compressive load.

Moisture Resistance

Minrock rockwool SPI are water repellant and do not absorb moisture by capillary action or ambient moisture from the atmosphere. Should they become wet, full thermal efficiency will be restored on drying out.

Corrosion Resistance

Will not cause, initiate or promote corrosion.

Fire Resistance

Minrockwool SPI are incombustible and resist scread of flames



Minwool Rock Fibres Ltd

BRANCHES

Baroda:

B/208, Prabhuta Complex, Near Darbar Complex, Near Darbar Chokdi, Manjalpur, Baroda-390 011. Mobile: 0265-2661992 E-mail: baroda@minwool.com

Chennai:

#6, Commerce Centre, 2nd Floor, 441 (Old No. 303) Annasalai, Teynampet Chennai-600 018 Ph: 044-243 35687 Telefax: 044-243 20709 E-mail: chennai@minwool.com

Coimbatore:

No.36/A, Chinna Swamynagar, Near Aavan Milk Booth, Ganapathi, Coimbatore - 641 006 Cell : +91 94434 78966

Kolkata:

Electronic Center, Room No. B-19, 1st Floor, 1/1A Biplabi, Anukul Chandra Street, Kolkata - 700 072. Ph. No.: +91 98302 71529 E-mail: kolkatta@minwool.com

Mumbai:

637, Laxmi Plaza, Laxmi Industrial Estate, New Link Road, Andheri (West), Mumbai-400 053. Telefax: 022-66924525/26324093 E-mail: bombay@minwool.com

New Delhi:

Flat No. 5, I Floor, Heritage Apartments, A-6, Naraina Vihar (Ring Road) New Delhi - 110 028. Ph : 011-45033200, 257 76425

Fax: 011-257 76401 E-mail: delhi@minwool.com

Pune:

Flat No. 7, III Floor Konark Court, 1505/11 Decsan College Road, Yerrawada Pune-411 006. Ph: 020-266 97962 Telefax: 020-266 84692

Surat :

75. Sardar Complex, Near Sardar Bridge, Adajan, Surat - 395 009. Ph. No.: 0261 - 2782363 E-mail: surat@minwool.com

Corporate & Hyderabad Office :

"GOPIKRISHN", # 8-2-598/A/1/15, Road No. 10, Banjara Hills, Hyderabad - 500 034.

Phone: 0091-40-23351114 / 5 & 7, Fax: 0091-40-23350462

E-mail: hyderabad@minwool.com